

## **Product Data Sheet**

## Flat Black Enamel - 0426

## **Product Description**

An alkyd based dead flat coating

### Where to Use

Used primarily on ornamental iron, heaters, or any utility type framing, etc. This product has good resistance to humidity, fumes, marking, and weather.

#### **Product Characteristics**

<u>Color</u> Black

Gloss Flat

Architectural and Industrial

Maintenance Category Not Intended for Residential Use, Shop Use Only

 Drying Time
 Temperature
 To Touch
 To Recoat

 75°F / 55% R.H.
 20 Minutes
 8 Hours

(Cooler temperatures and higher humidity will lengthen drying time)

### **Preparation & Priming**

Surface Preparation For maximum performance, the recommended substrate should be blasted in accordance with SSPC-SP7. If

blast cleaning is not feasible, the substrate should be degreased in accordance with SSPC-SP1. All burrs should be removed and sharp edges or rough weld seams should be ground down. Full use should then be made of mechanical power tools, in conjunction with wire brushing and chipping to remove all loose rust and

mill scale to a standard of cleanliness conforming to SP-2 or SP-3.

Finish Coats

Use Anchor #1730 Rust Inhibitive Primer Series, #0472 Fast Dry Primer or direct to metal. Consult your

Anchor representative for specific job recommendations.

#### Mixing & Application

Mixing Stir thoroughly, making sure no pigment remains on the bottom of the can.

This coating is VOC compliant; only thin if permitted by federal, state and local regulations. If necessary, use

Anchor #J1131 for spray applications or #J1112 for brush and roller usage.

Surface Temperature Minimum 40°F, Maximum 110°F - The surface should be dry and the relative humidity should be no greater

than 85%.

Recommended Thickness 1.6-2.0 mils dry per coat, two coats recommended

Theoretical Coverage will vary depending on the color,

application technique, porosity and design of the substrate.

 Minimum
 1.6
 3.5
 452

 Maximum
 2.0
 4.4
 362

Application Equipment Airless Spray Pressure 1200-2200 psi

Tip 0.011"-0.015"

Conventional Spray Air Pressure 60-80 psi

Fluid Pressure 10-20 psi

Brush Use a high quality natural china bristle brush.

Roller Use a 1/4" synthetic nap roller cover.

Application Considerations The recommended method of application is by airless spray. However, brush, roller, or conventional spray

may also be used. To avoid dusting, apply in wet coats. On a derusted surface the application of a dry film

thickness of at least 2 mils is recommended.

# Technical Information

Solids by Volume 45.09%

Coating VOC 3.60 lb/gal (431 g/l)

<u>Density</u> 10.61 lb/gal (1271 g/l)

Packaging 5 Gallon pails, 1 Gallon cans, and quart (1/4 gallon) cans

Physical Properties Alkalis: Poor Acids: Fair Water: Good

#### Clean-up & Storage

Cleanup Use Anchor #J1131 synthetic thinner

Storage Temperature Minimum 20°F Maximum 110°F

<u>Shelf Life</u> Under Normal Conditions (Unopened) – Two Years

## Safety & Important Information

DANGER! COMBUSTIBLE AND VAPOR. HARMFUL IF INHALED. CONTAINS: MINERAL SPIRITS. Vapor harmful. May affect the brain or nervous system causing dizziness, headache or nausea. Causes nose, eye, skin and throat irritation. Harmful if swallowed. NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.

Keep away from heat and flame. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation. **Use only with adequate ventilation.** Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. **KEEP OUT OF REACH OF CHILDREN.** 

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. WARNING! Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.

Version: 1/2012

LIMITED WARRANTY: The technical data on this label or on other data is true and accurate to the best of our knowledge. We guarantee our products to conform to ANCHOR PAINT MFG. CO. quality control standards. Due to misuse in handling, storage, application and workmanship or variables such as weather or surface integrity that are beyond our control, Anchor Paint does not authorize any representative to make any warranty or merchantability of fitness of this product. Any liability whatsoever of Anchor Paint Mfg. Co. to the buyer or user of this product is limited to the purchaser's cost of the product itself.