



# Product Data Sheet

## Rust Blok Enamelized Tank White - 2230

### Product Description

This durable enamel is formulated with a slow-chalking, pure titanium dioxide and a top grade vehicle resin. This coating has been manufactured to provide maximum resistance to the typical exposure to the elements endured by storage tanks.

### Where to Use

This product meets the requirements of SSPC No. 104 Type 1. It is generally applied on large storage tanks that are exposed to weathering but need to retain their white appearance.

### Product Characteristics

Color White

Gloss High Gloss

Architectural and Industrial Maintenance Category Industrial Maintenance Coatings

<u>Drying Time</u>	<b>Temperature</b>	<b>To Touch</b>	<b>To Recoat</b>
	75°F / 55% R.H.	1 Hour	8 Hours

(Cooler temperatures and higher humidity will lengthen drying time)

### Preparation & Priming

Surface Preparation For maximum performance, the recommended substrate should be blasted in accordance with SSPC-SP10. If blast cleaning is not feasible, the substrate should be degreased in accordance with SSPC-SP1. All burrs should be removed and sharp edges or rough weld seams should be ground down. Full use should then be made of mechanical power tools, in conjunction with wire brushing and chipping to remove all loose rust and mill scale to a standard of cleanliness conforming to SP-2 or SP-3.

Primer Coat Use Anchor #1703 Series Rust Inhibitive Primer or #1603 Series Rust Inhibitive Primer. Consult your Anchor representative for specific job recommendations.

### Mixing & Application

Mixing Stir thoroughly, making sure no pigment remains on the bottom of the can.

Thinning This coating is VOC compliant; only thin if permitted by federal, state and local regulations. If necessary, use Anchor #J1131 for spray applications and #J1112 for brush or roller applications.

Surface Temperature Minimum 50°F, Maximum 110°F - The surface should be dry and the relative humidity should be no greater than 85%.

Recommended Thickness 1.6-2.0 mils dry per coat, two coats recommended

Theoretical Coverage 835 ft<sup>2</sup>/gal at 1 mil dry, assuming no application losses. Coverage will vary depending on the color, application technique, porosity and design of the substrate.

<u>Coverage Rates per Coat</u>	<u>Dry Mils</u>	<u>Wet Mils</u>	<u>Ft<sup>2</sup>/gal</u>
<u>Suggested</u>	1.8	3.5	464
<u>Minimum</u>	1.6	3.1	522
<u>Maximum</u>	2.0	3.8	418

<u>Application Equipment</u>	<u>Airless Spray</u>	
	Pressure	1200-2200 psi
Tip	0.011"-0.015"	
<u>Conventional Spray</u>	Air Pressure	40-70 psi
	Fluid Pressure	10-20 psi

Application Considerations Brush, roll, or spray. The recommended method of application is by airless spray. However, to avoid dusting, apply in wet coats. Use cross-hatch method, overlapping each pass 50%. Clean system thoroughly before and after each use. On a derusted surface the application of a dry film thickness of at least 2 mils is recommended.

**Technical Information**

<u>Solids by Volume</u>	52.08%		
<u>AIM Category VOC Limit</u>	3.8 lb/gal (450 g/l)		
<u>Actual VOC</u>	3.10 lb/gal (371 g/l)		
<u>Density</u>	11.51 lb/gal (1379 g/l)		
<u>Packaging</u>	55 Gallon drums, 5 Gallon pails and 1 Gallon cans		
<u>Physical Properties</u>	<u>Alkalis:</u>	Fair	<u>Acids:</u> Good
			<u>Water:</u> Excellent

**Clean-up & Storage**

<u>Cleanup</u>	Use Anchor #J1131 synthetic thinner	
<u>Storage Temperature</u>	Minimum 20°F	Maximum 110°F
<u>Shelf Life</u>	Under Normal Conditions (Unopened) – Two Years	

**Safety & Important Information**

DANGER! EXTREMELY FLAMMABLE LIQUID AND VAPOR. CONTAINS: MINERAL SPIRITS AND PETROLEUM DISTILLATES. Vapor harmful. May affect the brain or nervous system causing dizziness, headache or nausea. Causes nose, eye, skin and throat irritation. NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.

Vapors may ignite explosively. Keep away from heat, sparks and flame. Vapors may cause flash fire. Close container after each use. Do not smoke. Extinguish all flames and pilot lights, and turn off stoves, heaters, electric motors and other sources of ignition during use and until all vapors are gone. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation. **Use only with adequate ventilation.** Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. **KEEP OUT OF REACH OF CHILDREN.**

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). WARNING! Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.

Version: 1/2012

**LIMITED WARRANTY:** The technical data on this label or on other data is true and accurate to the best of our knowledge. We guarantee our products to conform to ANCHOR PAINT MFG. CO. quality control standards. Due to misuse in handling, storage, application and workmanship or variables such as weather or surface integrity that are beyond our control, Anchor Paint does not authorize any representative to make any warranty or merchantability of fitness of this product. Any liability whatsoever of Anchor Paint Mfg. Co. to the buyer or user of this product is limited to the purchaser's cost of the product itself.