

# **Product Data Sheet**

# XP Acrylic Alkyd Enamel – 6000 Series

## **Product Description**

A Low VOC and HAPS, guick drying, high-solids, acrylic enamel developed for agricultural, construction and industrial machinery and small transportation.

#### Where to Use

Typical uses include original equipment machinery and other production line applications. For use where a VOC compliant coating is required in place of present conventional coatings such as Saf-T-Gard or Quick Touch enamels.

## **Product Characteristics**

Color #6000 - White, #6001 - Black, #6003 - Red, #6019 - Blue and Custom Colors

Gloss High Gloss

Architectural and Industrial

Maintenance Category **Quick Dry Coatings** 

Temperature To Touch To Recoat **Drying Time** 75°F / 55% R.H 50 Minutes 30 Minutes to 2 Hours (Otherwise Wait 7 Days)

(Cooler temperatures and higher humidity will lengthen drying time)

#### **Preparation & Priming**

Surface Preparation For maximum performance, the recommended substrate should be blasted in accordance with SSPC-SP6

commercial blast. If blast cleaning is not feasible, the substrate should be degreased in accordance with SSPC-SP1. All burrs should be removed and sharp edges or rough weld seams should be ground down. Where weathered steel is applicable and where substrate has reached rust grade, the appropriate chemical

cleaning or blasting will be necessary.

Primer Coats This product is recommended for use over Anchor LoVOC Primer #B7911 or LoHAPS versions #CC0655 and

#CC0658. This product is designed to be applied over barrier type primers or intermediate coats. When this is not possible, the coating can be applied directly to clean metal making sure a maximum millage of 2.0 mils dry per coat is applied. Each service environment may require a specific coating system or combination of

Anchor products. Consult your Anchor representative for specific job recommendations.

#### Mixing & Application

Stir thoroughly, making sure no pigment remains on the bottom of the can. **Mixing** 

**Thinning** This coating is VOC compliant; only thin if permitted by federal, state and local regulations. If necessary, use

T0050M, a no HAPS solvent, only up to 15%.

Minimum 50°F, Maximum 110°F - The surface should be dry and the relative humidity should be less than Surface Temperature

Recommended Thickness 1.6-2.0 mils dry per coat. Apply one tack coat and then proceed with two full coats.

**Theoretical Coverage** 837 ft²/gallon at 1 mil dry, assuming no application loss. Coverage will vary depending on surface texture

and application technique.

Coverage Rates per Coat Dry Mils Wet Mils Ft2/gal 1.8 465 Suggested 3.4

16 523 Minimum 3 1 **Maximum** 2.0

Pressure 1200-2200 psi Application Equipment Airless Spray

> 0.011"-0.015" Tip

Conventional Spray Air Pressure 60-80 psi

> Fluid Pressure 10-20 psi

# **Mixing & Application Continued**

**Application Considerations** 

This material dries very fast. This coating will build much faster than conventional enamels such as Quick Touch. Use caution when applying to avoid excessive film build. Start with a 0.013" tip orifice and pressures that allow for wet coat without dusting or blow-out. Adjust tip and pressure settings as necessary. Where air quality regulations allow, thin only if necessary up to 15.0% or until material atomizes at the tip. Apply in wet coats to avoid dusting. When spraying, use a cross-hatch method, overlapping each pass 50%. Clean spray system thoroughly before and after each use. On a derusted surface, the application of a dry film of at least 2.0 mils is recommended.

#### **Performance Data**

Solids by Volume 52.18% – Varies by Color

AIM Category VOC Limit 3.8 lb/gal (450g/l)

Actual VOC 3.27 lb/gal (394 g/l) – Varies by Color

<u>Density</u> 9.76 lb/gal (1169 g/l) – Varies by Color

Packaging 55 Gallon drums, 5 Gallon pails and 1 Gallon cans

<u>Chemical Resistance</u> <u>Alkalis:</u> Fair <u>Acids:</u> Good <u>Water:</u> Good

Heat Resistance 150°F Continuous, 250°F Spikes

# Clean-up & Storage

Cleanup Use Anchor #T0050M

Storage Temperature Minimum 20°F Maximum 110°F

Shelf Life Under Normal Conditions (Unopened) – Two Years

#### Safety & Important Information

WARNING! FLAMMABLE LIQUID AND VAPOR. VAPOR HARMFUL. CONTAINS: METHYL N-AMYL KETONE, METHYL PROPYL KETONE AND PETROLEUM DISTILLATES. Vapor harmful. May affect the brain or nervous system causing dizziness, headache or nausea. Causes nose, eye, skin and throat irritation. Harmful if swallowed. NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.

Keep away from heat, sparks and flame. Vapors may cause flash fire. Do not smoke. Extinguish all flames and pilot lights, and turn off stoves, heaters, electric motors and other sources or ignition during use and until all vapors are gone. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation. Use only with adequate ventilation. Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin or clothing. Wash thoroughly after handling. KEEP OUT OF REACH OF CHILDREN.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. WARNING! Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.

Version: 1/2018

LIMITED WARRANTY: The technical data on this label or on other data is true and accurate to the best of our knowledge. We guarantee our products to conform to ANCHOR PAINT MFG. CO. quality control standards. Due to misuse in handling, storage, application and workmanship or variables such as weather or surface integrity that are beyond our control, Anchor Paint does not authorize any representative to make any warranty or merchantability of fitness of this product. Any liability whatsoever of Anchor Paint Mfg. Co. to the buyer or user of this product is limited to the purchaser's cost of the product itself.