



LO SHEEN QUICK DRY ENAMEL, #AA-1266

PRODUCT PROFILE

General Description

This is a fast drying alkyd enamel that provides a decorative and durable mar-resistant coating. Due to its low luster and dense film, it will not hold dirt as flat materials will do.

Common Usage

Areas such as ducting, joists and ceilings where the fallout or overspray dries within a few feet so that it does not adhere to unprotected surfaces. This product is not intended for direct exposure to weather.

Color

White

Finish

Low Sheen

COATING SYSTEMS

Primer Coat

Use Anchor #472 Gray, #2653 Red Fast Dry Primers or direct to metal. Consult your Anchor representative for specific job recommendations.

SURFACE PREPARATION

Surface must be dry and free of all dirt, grease, oil, failing paint, etc. On previously painted surfaces, test for lifting by applying in a small area and allowing to cure while watching for wrinkling or seperating. Designed to be applied over primer. When not feasible, it may be applied directly over substrate making sure a maximum recommended millage is obtained.

TECHNICAL DATA

Volume Solids

35.64%

Recommended Thickness

2.0 mils dry minimum.

Drying Time

<u>Temperature</u>	<u>To Touch</u>	<u>To Recoat</u>
75 F / 55% R.H.	20 minutes	1 hour

(Cooler temperatures and higher humidity will lengthen drying time)

Architectural and Industrial Maintenance Category

Not Intended for Residential Use; Shop Use Only

Actual V.O.C.

4.53 lbs./gal. (543.6 g/l)

Theoretical Coverage

572 sq. ft./gallon @ 1 mil dry, assuming no application loss. Coverage will vary depending on surface texture and application technique.

Packaging

5 Gallon pails, and 1 Gallon cans

Storage Temperature

Minimum 20 F Maximum 110 F

Chemical Resistance

<u>Alkalis</u>	Poor
<u>Acids</u>	Good
<u>Water</u>	Good

**F
A
S
T

D
R
Y

L
O
W

G
L
O
S
S

/

W
H
I
T
E**



Health & Safety

Refer to the product label itself and your Anchor representative concerning a Material Safety Data Sheet for complete information on this product.

APPLICATION

Coverage Rates Per Coat

	<u>Dry Mils</u>	<u>Wet Mils</u>	<u>Sq.Ft./ Gal.</u>
<u>Suggested</u>	2	5.6	286
<u>Minimum</u>	2	5.6	286
<u>Maximum</u>	3	8.4	190

Mixing

Stir thoroughly, making sure no pigment remains on the bottom of the can.

Thinning

Use Anchor #J-1131 or #J-34 Fine Finish Blend.

Surface Temperature

Minimum 50 F Maximum 110 F
The surface should be dry and the relative humidity should be less than 85%.

Application Equipment

<u>Airless Spray</u>	Pressure	1200-2200 psi
	Tip	.011"-.015"
<u>Conventional Spray</u>	Air Pressure	40-70 psi
	Fluid Pressure	10-20 psi

Cleanup

Use Anchor #J-1131 synthetic thinner.

Application Considerations

Spray application only. Apply in wet coats to avoid dusting. When spraying, use cross-hatch method, overlapping each pass 50%. Clean system thoroughly before and after each use. On a derusted surface the application of a dry film thickness of at least 2 mils is recommended.

LIMITED WARRANTY

The technical data on this label or on other data is true and accurate to the best of our knowledge. We guarantee our products to conform to ANCHOR PAINT MFG. CO. quality control standards. Due to misuse in handling, storage, application and workmanship or variables such as weather or surface integrity that are beyond our control, Anchor Paint does not authorize

any representative to make any warranty or merchantability of fitness of this product. Any liability whatsoever of Anchor Paint Mfg. Co. to the buyer or user of this product is limited to the purchaser's cost of the product itself.